

#### Thermocoat WO

### THERMOCOAT WO INTUMESCENT PAINT FOR STRUCTURAL STEEL AND CAST IRON

#### **Key Benefits:**

Thermocoat WI is a low-odour, water-based coating, making it user and environmentally friendly. The range of topcoats are either water-based or 2010 compliant and safe to use in accordance with manufacturer's instructions.

Dry Internal: Apply Thermocoat WO in accordance with Thermoguard film thickness schedule to achieve 30, 60, 90 minutes. Visible or occasional modest damp internal areas:

Also apply 1 good coat Thermoguard Flame Retardant Gloss or Eggshell or Dualcoat SFR Matt or Eggshell

Wet or External Under Cover: Apply 2 coats Thermoguard Flame Retardant Gloss or Eggshell

Full External Exposure: Contact Technical Dept.

Thermocoat WO can be topcoated with Flame Retardant gloss, eggshell, Dualcoat SFR Matt , Dualcoat SFR Eggshell BS 4800 & RAL colours

### **Intended Use:**

Thermocoat WO is optimised to protect hollow posts. It is a water-based intumescent paint system providing fire resistance to structural steel and cast iron of up to 90 minutes with a minimum number of coats. A compatible decorative overcoat system ensures the system will enhance the building's architectural and design features.

**How it works:** The heat of a fire triggers a catalytic reaction, causing the expansion of an insulating char layer up to 50 times the paint thickness. This layer keeps the steel below its critical temperature, thus maintaining the structural integrity of the building.

## **Pack Sizes:**

Available in 20kg, 5kg, 2.5kg

## Coverage:

Prior to application the contractor should contact Thermoguard's Technical Department and obtain a basecoat application schedule or follow on can guidance. Do not overspread as this will compromise the system and result in non-compliance and a failure to be certified

# **Drying Times:**

Brush/roller application Surface dry: minimum 2 hours

Recoat: minimum 4 hours

Overcoating with Flame Retardant finish: minimum 10 hours

Spray Application Surface Dry: minimum 4 hours

Recoat: minimum 10 hours

Overcoating with Flame Retardant finish: minimum 48 hours

## **Preparation:**

Steel and cast iron should be free from rust and millscale and primed with Thermoguard Steel Fire Paint Primer to 75 microns DFT (or alternative good quality anti-corrosive primer compatible with intumescent paints) in accordance with manufacturer's instructions. Treat galvanised surfaces with "T" wash/Mordant solution & prime with zinc phosphate or other primer for steel.

## **Application Conditions:**

Maximum Relative Humidity 80% Minimum ambient temperature 4°C Minimum Steel Temperature 3°C above Dew Point



### Thermocoat WO

### Application:

Thermocoat WO may be applied by brush, roller or airless spray. To achieve the best finish in the shortest time, spray application is recommended. Prior to application the contractor should contact Thermoguard's Technical Department and obtain a basecoat application schedule. To assist correct application in accordance with this schedule, a wet film gauge will be supplied with the order. Further wet film gauges will be provided on request.

Maximum wet film thickness per brush coat - 800 microns

Maximum wet film thickness per spray coat - 1400 microns

## Spray:

Spray Equipment- Airless Spray Pump

Use equipment recommended by manufacturer for the application of high viscosity intumescent paints.

Filter size 30 mesh. 10mm hose 3/8" diameter with no whip end.

Tip Size 319, 321, 419, 421

Care should be taken to clean filters regularly. Cleaning should be undertaken with water.

### **Fire Certification:**

Thermoguard issue a Certificate of Supply on request for each specified project for insurance, Fire and Building Control Authority and Client Records.

**VOC Content:** EU limit for this product (cat A/i) is 140 g/l. This product contains 16 g/lv

### Composition:

Intumescent compounds and resin binders, with high opacity pigments.

## **Test Data:**

Product performance assessment is based upon UKAS/ EGOLF Fire Test Laboratory Certification to BS 476 Part 21 - Fire Resistance to load bearing elements of structures.

## **Health And Safety:**

Please refer to the relevant Safety Data Sheet for full details of this product.

Apply all products in accordance with BS 6150:2019- Code of practice for painting of buildings.

Do not store this product in cold temperatures below 5°C or above 30°C.

Store in a dry secure place away from children or animals. Dispose of in accordance with local authority waste disposal measures. Do not pour into drains or watercourses.

Technical Department 01142 768008 or email technical@thermoguard.co.uk

**Technical Advisory and Estimating Service** Thermoguard's in-house estimators provide realistic, confidential guidance on project costings to contractors and quantity surveyors. They also provided expert advice and assistance with all aspects of specification and application.

All materials and specifications are provided in accordance with the T & C's of Thermoguard Refer to Health & Safety Data Sheets on www.thermoguard.co.uk before using these products.